

CARBON STEELS*NONRESULFURIZED*

(Manganese maximum over 1.00 per cent)

<u>AISI or SAE #</u>	<u>C</u>	<u>Mn</u>	<u>P Max</u>	<u>S Max</u>
1513	.10/ .16	1.10/ 1.40	0.040	0.050
1522	.18/ .24	1.10/ 1.40	0.040	0.050
1524	.19/ .25	1.35/1.65	0.040	0.050
1526	.22/ .29	1.10/ 1.40	0.040	0.050
1527	.22/ .29	1.20/1.50	0.040	0.050
1536	.30/ .37	1.20/1.50	0.040	0.050
1541	.36/ .44	1.35/1.65	0.040	0.050
1548	.44/ .52	1.10/1.40	0.040	0.050
1551	.45/ .56	.85/1.15	0.040	0.050
1552	.47/ .55	1.20/1.50	0.040	0.050
1561	.55/ .65	.75/1.05	0.040	0.050
1566	.60/ .71	.85/1.15	0.040	0.050